



SBR LATEX

BONDING ADMIXTURE

DESCRIPTION

SBR LATEX is a carboxylated styrene butadiene copolymer latex admixture that is designed as an integral adhesive for cement bond coats, mortars and concrete to improve bond strength and chemical resistance.

PRIMARY APPLICATIONS

- Toppings, repairs and leveling concrete surfaces
- Thin sets, terrazzo, stucco and bonding coats
- General reconstruction work/latex modified overlays
- Bridge decks, highways and parking decks

FEATURES/BENEFITS

- Reduces cracking through increased mortar flexural strength
- Improves bond strengths to hardened concrete
- Increases wear resistance under rubber wheeled traffic
- Increases durability during freeze/thaw cycles
- Increases mortar tensile strength

TECHNICAL INFORMATION

Property	SBR Latex-Modified Mortar
Compressive Strength, MPa ASTM C 109	3 days: 25 7 days: 32 28 days: 37
Flexural Strength @ 7 days, MPa ASTM C 78	3 days: 10 7 days: 15
Tensile Strength, 7 days, MPa ASTM C 190	3 days: 3 7 days: 3.8
Appearance	White liquid

SBR LATEX-Modified Mortar Mix Design:

Type I Portland Cement 50 kg
Sand 150 kg
SBR LATEX 8 L
Water 3.50 L

Property of SBR Latex	Value
Unit Weight	1.0 kg/L
Solids Content by Weight	48%
pH	10 to 11

PACKAGING

SBR LATEX is packaged in 210 Kg drums, 20 Kg pails

SHELF LIFE

1 year in original, unopened package.

SHELF LIFE

Complies with ASTM C 1059-86, Type II

SBR LATEX is classified by The American Concrete Institute as a non-re-emulsifiable bonding admixture Canadian MTQ

COVERAGE

	Bond Coat	Cementitious Mortar	Concrete Topping
Cement	50 Kg	50 Kg	295.5 kg
Sand	—	150 Kg	700 kg
#8 Coarse Aggregate	—	—	645 Kg
SBR LATEX	13.5 L	8.9 to 17.7 L	38.5 to 46.09 L
Water	22 to 26.5 L	8.9 to 17.7 L	83.16 to 90 L
Total Liquid	35 to 39 L	22.3 to 27 L	84.43 to 100 L
Yield	75 m ²	0.16 m ³	0.72 m ³

Coverage:

Bond Coat: 700 to 940 ft² (65 to 87 m²) Cementitious Mortar: 117 to 140 ft² (11 to 13m²) @ 12.7 mm

Concrete Topping: 152 to 162 ft² (14 to 15 m²) @ 50 mm

Coverage rates are estimates only and is highly dependent upon concrete texture and unit weight of aggregate used.

DIRECTIONS FOR USE

Surface Preparation: If using this product as a cementitious bond coat, the base concrete must be a minimum of 3 days old. The concrete must be clean and all oil, dirt, debris, paint, curing compounds, sealers and unsound concrete must be removed. The surface must be prepared mechanically using a scabber, bushhammer, shotblaster or scarifier, so that the minimum surface profile is 3 mm and exposes the large aggregate of the concrete. **Note: Acid etching is not acceptable.** Finally, clean the concrete of all residue with a vacuum cleaner and/or pressure washer. Allow the concrete surface to begin drying, and do not place the cementitious bond coat on standing water. Base concrete must be saturated-surface dry (SSD) to reduce moisture loss.

Bonding: For bonding toppings with this product, The Euclid Chemical Company strongly recommends using a cement bond coat rather than using this product as a primer by itself. After the surface has been prepared, prime all areas with a bond coat before the topping is applied. Follow mixing and placing instructions listed below. Place the topping on the bond coat before the bond coat dries out.

Mixing: Small quantities may be mixed with a drill and "jiffy" mixer. Use a paddle type mortar mixer for large jobs. All materials should be in the proper temperature range of 5^o C to 32^o C. Add the appropriate amount of SBR LATEX for the batch size and then add the dry material. If using SBR LATEX with a pre-packaged product, reduce the amount of water added to compensate for the latex addition. Mix a minimum of 3 minutes. The mixed product should be quickly transported to the repair area and placed immediately. Placement: Discharge material onto the floor.

Bond Coat Application: Spread the bond coat with a stiff bristle broom until the suggested coverage rate is achieved.

Topping Application: For patching, spread with a trowel, come-a-long, or square tipped shovel to a thickness that matches the surrounding concrete. Finish by hand troweling. On large floor areas, use screed strips as guides in combination with vibratory screeding to level. Compact and finish by hand or machine trowel.

Finishing: Finish the repair material to the desired texture. Typical texture is a broom or sponge float finish. Do not add additional water to the surface during the finishing operation. If additional liquid is required, use EU COBAR finishing aid.

Curing: Proper curing procedures are important to ensure the durability and quality of the repair or overlayment. To prevent surface cracking, a moist cure should be maintained for 24 hours followed by use of a curing compound such as DIAMOND CLEAR VOX or AQUA-CURE VOX. **Do not use a solvent based curing compound on latex modified mortars.**

CLEAN-UP

Clean tools and equipment with water before the material hardens.

PRECAUTIONS/LIMITATIONS

- Do not use material at temperatures below 7°C. Protect from freezing.
- No heavy traffic until the product has cured.
- Not designed for use on its own as a bonding agent. SBR LATEX must be used in a slurry with portland cement.
- Use of this product in conjunction with air entrained cement/concrete or with other admixtures may significantly increase total entrained air content. Testing is strongly advised.
- Do not use a solvent based curing compound on latex modified mortars.
- In all cases, refer the Safety Data Sheet before use.

WARRANTY: Flowcrete India Private Limited solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Flowcrete India Private Limited no other representations or statements made by Flowcrete India or its representatives, in writing or orally, shall alter this warranty. Flowcrete India MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Flowcrete India product fails to conform with this warranty, Flowcrete India will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any installation of Flowcrete India products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Flowcrete India's products for the Buyer's intended purposes.