



PLASTOL ULTRA 209

HIGH RANGE WATER REDUCING ADMIXTURE

DESCRIPTION

PLASTOL ULTRA 209 high-range water-reducing and superplasticizing admixture is formulated using advanced polycarboxylate technology, specifically engineered for concrete to provide maximum water reduction, slump, flow, and improved finishing characteristics while maintaining consistent air contents from initial batching to final placement. In addition, PLASTOL ULTRA 209 provides high compressive strengths, flexural strength, and excellent setting characteristics. PLASTOL ULTRA 209 can be used to reduce the total cement content and used in combination with supplementary cementitious materials. PLASTOL ULTRA 209 does not contain added chlorides or chemicals known to promote the corrosion of steel.

PRIMARY APPLICATIONS

- Precast/pre-stressed concrete
- Self-Consolidating Concrete (SCC)
- High slump, flowable concrete
- Low water to cement ratio concrete
- High early strength concrete
- Ready-mix concrete
- Flatwork and mass concrete
- Pervious concrete

FEATURES/BENEFITS

- Superior slump gain
- Consistent control of air content
- Improved cement hydration
- Low dosage
- Higher early and ultimate strengths
- Lowers number of rejected concrete loads
- Quicker stripping times
- Aids in concrete placement and reduces labor cost
- Improved finishability

TECHNICAL INFORMATION

Performance Data	
Specific Gravity	1.09 ± 0.02 @25°C
Physical State	Light brown liquid
Base Material	Polycarboxylate
Air entrainment	±1.5% over control mix
pH	Min 6
Chloride Content	<0.2 %

Compatible with all cement types like OPC, OPC+fly ash, PPC etc.,

PACKAGING

PLASTOL ULTRA 209 is packaged in bulk 220 Kg.

SHELF LIFE

1 Year in original, unopened container.

SPECIFICATIONS/COMPLIANCES

- Confirms the requirements of IS 9103/2007
- ASTM C 494, Type A, F
- AASHTO M 194

DIRECTIONS FOR USE

Normal dosage range is 200 ml - 600 ml/50 kg of cement. However the optimum dosage is determined by site trials. PLASTOL ULTRA 209 should be added to initial batch water of the concrete mixture. Do not dispense on to dry cement. Over dosing leads to retardation of setting times of concrete, Mix may segregate and bleeding of concrete.

PRECAUTIONS/LIMITATIONS

- Care should be taken to maintain PLASTOL ULTRA 209 above freezing, however, freezing and subsequent thawing will not harm the material if thoroughly agitated.
- Do not agitate with air.
- Add to concrete mix independent of other admixtures.
- In all cases, refer the Safety Data Sheet before use.

WARRANTY: Flowcrete India Private Limited solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Flowcrete India Private Limited no other representations or statements made by Flowcrete India or its representatives, in writing or orally, shall alter this warranty. Flowcrete India MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Flowcrete India product fails to conform with this warranty, Flowcrete India will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any installation of Flowcrete India products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Flowcrete India's products for the Buyer's intended purposes.