

DIRECTIONS FOR USE

Surface Preparation

General – Surface should be sound, clean and free of dust, oil, grease and curing compound. Loosely adhered particles such as rust scale, cement smears should be thoroughly cleaned with a wire brush or another such implement. Concrete all new concrete surfaces must be fully cured (6-8 weeks) with a semi- rough surface appearance. Rendered surfaces must be allowed to cure for a minimum of 7 days prior to the commencement of waterproofing. All surfaces must as level as possible with a slope variation not exceeding 4mm. Gypsum/Plasterboard sheets must be installed to the manufacturer's guidelines with all joints being covered with a 50mm wide PP or PE tape whilst all screw/nail heads must be sealed with epoxy. When used as a wall substrate, sheet thickness should be a minimum 10mm thick. Fibre Cement sheets when used as a floor/wall underlay sheets should be a minimum 6mm thick whilst compressed fibre cement sheets should be a minimum 9mm thick for walls and 15mm thick for floor applications. Metal Surfaces ensure surfaces are rust free with any hairline cracks being filled with a suitable gap filler whilst cracks larger than 2mm should be filled.

Priming All surfaces to be primed with the same product diluted with 20% water whilst metal surfaces need to be primed with suitable water based primer. The primer can be applied with a brush, roller or squeegee depending on the size of the area required to be primed. Allow 10–30 minutes at a temperature of 20 °C for the primer to dry before commencing to waterproof with Tammsflex WP.

METHOD OF APPLICATION

Remove all loose material by vigorous brushing, wire brush if necessary.

Treat any fungal growth with proprietary fungicide as recommended.

Allow surface to clean.

Fill cracks and voids with mastic sealants.

Prime with PRIMER (6 - 12 m / lt depending on substrate porosity) which within 1-3 hours.

Once the primer is completely dry then apply first coat which when dried follow it up with the second coat at 90° right angles to the first coat ensuring a complete coverage. Please note that air bubbles trapped under the surface must be removed in order to achieve the maximum waterproofing effect. Apply third coat if require NOTE : PLEASE DO NOT DILUTE ANY COAT AFTER THE PRIMER IS APPLIED Tammsflex WP-IN requires to applied at minimum thickness of 1.2 mm of DRY FILM THICKNESS (DFT) in 2 coats Apply a minimum 1litrecoverage @ 0.9 sq/m per coat in two coats perpendicular to each other over a primed surface In case of multi-coat application, the previous coat should be touch dry depending on the weather conditions). Ensuring that the surface is smooth and without any pinholes allow 24 hours at 20 °C before commencing to apply a suitable tile adhesive. Please note that a third coat may be required if any imperfections are present in the membrane. Tammsflex WP-IN can be applied by brush or roller without the need to mix, stir or heat before application.

SUPPLEMENTARY NOTES

- The dry film thickness (DFT) of Tammsflex WP-IN should not be less than 0.55mm or more than 1.0mm for each coat. Rough surfaces will reduce the coverage rate and consequently more material must be allowed to achieve the minimum DFT. Surfaces previously treated with silicone-based materials will inevitably be difficult to overcoat and this should not be attempted with Tammsflex WP Substrates with poor adhesion to the underlying structure (e.g. blistered roofing felt) may also cause problems in providing sound over-coating.
- Preferential vapour drive in buildings must also be borne in mind when over- coating the roof and it may be judged expedient to employ ventilation to cope with transmission of high levels of moisture vapour. Coverage rates may vary with surface and porosity. The information given is based on average usage. A site trial is recommended. Minor damage to Tammsflex WP-IN can be repaired by removing loose membrane; cleaning the surrounding area with water; overlapping by 150mm; priming the area with PRIMER and finishing with two coats of Tammsflex WP.
- Tammsflex WP-IN is available in various colours on request..
- Tammsflex WP-IN works best when it is applied when the temperature is between 5°C and 40°C

ENVIRONMENT & HEALTH

Follow the appropriate Occupational Health & Safety guidelines applicable to the location where the application is undertaken. For more information, Please refer to the safety sheet attached