# **FORMSHIELD PURE-IN**

**OIL-BASED CONCRETE FORM RELEASE** 



# **DESCRIPTION**

FORMSHIELD PURE-IN is a concrete form release agent with exceptional performance and ease of use that is unmatched by oil-based form release products. FORMSHIELD PURE-IN has a unique crystal clear formulation containing a proprietary ingredient that provides release capability superior to traditional form oils. Metal, plastic, wood and composition forms strip cleanly with FORMSHIELD PURE-IN.

# **PRIMARY APPLICATIONS**

· Preventing the adhesion of concrete to forms of all types

## **FEATURES/BENEFITS**

- Forms release easily and cleanly from concrete
- No staining
- Dramatically reduces the occurrence of voidsand bugholes
- · Very low odour

- Tolerant to freezing conditions during storageand transportation
- Treated forms are ready for use quickly
- Easy storage and shipping.

## **TECHNICAL INFORMATION**

PROPERTY	RESULT
Specific Gravity	0.82-0.84 @ 27°C

# **PACKAGING**

FORMSHIELD PURE-IN is packaged in 200 litre drum and 20 litres container.

## SHELF LIFE

1 years in original, unopened container.

## **COVERAGE**

Plywood Forms/Wood  $20 \text{ m}^2/\text{L}^2$  Composition Forms  $\text{Metal Forms} \qquad \qquad 40\text{-}60 \text{ m}^2/\text{L}^2$ 

**Note:** Coverage rates are approximate and for estimating purposes only. Surface temperature, porosity and texture will determine actual material requirements.

## **DIRECTIONS FOR USE**

**Surface Preparation:** The form surface must be free from dirt, cement paste, hardened concrete and other residue that could transfer to the finished concrete surface. Before coating plywood forms, apply a heavy brush coat to the plywood edges to protect laminations.

**Application:** In cold weather or if FORMSHIELD PURE-IN has been stored in a cold location, gently stir the product before using. FORMSHIELD PURE-IN can be applied by brush, spray or roller. Apply in a continuous film, avoiding excessive buildup, runs and puddles. Forms treated with FORMSHIELD PURE-IN will be ready to use within one hour on plywood and 2 to 3 hours on metal and plastic forms. Used forms can be re-coated with FORMSHIELD PURE-IN if proper surface preparation techniques are followed.

# **COVERAGE**

Clean tools and application equipment immediately after use with mineral spirits. Clean drips and overspray while still wet.

## **PRECAUTIONS/LIMITATIONS**

- Do not thin or dilute FORMSHIELD PURE-IN.
- The viscosity of FORMSHIELD PURE-IN increases at low temperatures, resulting in reduced sprayability.
- In all cases, refer the Safety Data Sheet before use.