



EUCOREPAIR V100

SINGLE-COMPONENT, LOW SHRINKAGE,
VERTICAL/OVERHEAD REPAIR MORTAR

DESCRIPTION

EUCOREPAIR V100 is a single-component, quick-setting, low shrinkage repair mortar formulated with unique polymers and fiber reinforcement for trowel applied vertical and overhead repairs requiring high performance.

PRIMARY APPLICATIONS

- Vertical and overhead repairs
- Resurfacing of damaged/deteriorated concrete
- Marine structures, tunnels and dams
- Parking structures & bridges
- Above and below grade applications

FEATURES/BENEFITS

- Single-component for easy mixing and handling
- Excellent freeze-thaw resistance for difficult climates
- Polymer modified with fiber reinforcement
- Contains an integral corrosion inhibitor
- Low permeability helps protect rebar from corrosion
- High bond strength provides excellent adhesion

TECHNICAL INFORMATION

Typical Engineering Data @ 24°C, 50% RH

PROPERTIES	RESULT	
Compressive Strength ASTM C 109 modified 2" (5 cm) cubes, MPa	3 hours	13.8 MPa
	1 day	20.7 MPa
	7 days	31.0 MPa
	28 days	41.4 MPa
Split Tensile Strength ASTM C 496, MPa	1 day	>1.4 MPa
	7 days	>1.7 MPa
	28 days	>2.8 MPa
Flexural Strength ASTM C 348, MPa	1 day	>2.8 MPa
	7 days	>3.4 MPa
	28 days	4.1 MPa
Bond Strength ASTM C 882, MPa	7 days	>9.7 MPa
	28 days	>12.4 MPa
Modulus of Elasticity ASTM C 469, psi MPa	28 days	1.83 x 10 ⁴ MPa
Length Change ASTM C 157 modified (3"x3"x11.25" specimens)	28 days	-0.020%
Unit Weight	28 days	1,922 kg/m ³
Set Times	Initial: ~ 20 min. Final: ~ 35 min.	

Appearance: EucoRepair V100 is a free-flowing powder designed to be mixed with water. After mixing and placing, the color may appear darker than the surrounding concrete. While this color will lighten as the EucoRepair V100 cures and dries out, the repair may always appear darker than the surrounding concrete.

PACKAGING/YIELD

EucoRepair V100 is packaged in 25 kg moisture resistant bags. 13.4 litre per 25 kgs bag

COVERAGE

One unit of EucoRepair V100 will cover approximately 1.0 m² when placed at an average depth of 13 mm.

SHELF LIFE

1 year in original, unopened package

DIRECTIONS FOR USE

Surface Preparation: Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a surface profile equal to CSP 5 - 7 in accordance with ICRI Guideline 310.2. Properly clean profiled area. Priming: Clean and prime exposed steel with DURALPREP AC. Concrete should be primed with a spray or brush coat of DURALPREP AC. The primer coat of DURALPREP AC must be allowed to thoroughly dry prior to the application of EucoRepair V100. Alternatively, a Saturated Surface Dry (SSD) concrete surface can be primed with a scrub coat of EucoRepair V100. The repair must be made before the scrub coat dries out.

Mixing: Single bags may be mixed with a drill and "jiffy" type mixer. Use a paddle type mortar mixer for large jobs. All materials should be in the proper temperature range of 16°C to 32°C. Add the appropriate amount of water, 4.0 to 4.5 L/bag into a clean mixing vessel, then add the dry product. Mix for 3 to 5 minutes. Do not mix more material than can be placed within 15 minutes.

Placement: Place in 3 to 100 mm lifts for vertical surfaces and 3 to 50 mm lifts for overhead applications. Trowel into place and allow to reach final set before the next lift. If additional lifts are required, score the surface of the placed mortar before it reaches final set.

Finishing: Finish the repair material to the desired texture. Do not add additional water to the surface during the finishing operation. Use EUCOBAR evaporation retarder.

Curing and Sealing: Curing is required. Cure with a Euclid Chemical high solids, water-based curing compound. (NOTE: A SOLVENT BASED CURING COMPOUND SHOULD NOT BE USED ON THIS PRODUCT). Under hot, windy or direct sunlight situations, apply a second coat of curing compound after the first has dried. If a curing compound is not desired, wet cure for a minimum of three days.

CLEAN-UP

Clean tools and equipment with water before the material hardens.

PRECAUTIONS/LIMITATIONS

- Do not allow repairs to freeze until the material has reached a minimum of 7 MPa compressive strength.
- In adverse temperatures, follow ACI recommendations for hot/cold weather concrete practices.
- Use only potable water for mixing.
- Minimum application thickness 3 mm.
- Minimum surface and ambient temperature 7°C and rising at time of application.
- For optimum results, condition material to 18°C to 29°C at least 24 hours prior to use.
- Do not use a solvent based curing compound on this product.
- In all cases, refer the Safety Data Sheet before use.

WARRANTY: Flowcrete India Private Limited solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Flowcrete India Private Limited no other representations or statements made by Flowcrete India or its representatives, in writing or orally, shall alter this warranty. Flowcrete India MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Flowcrete India product fails to conform with this warranty, Flowcrete India will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any installation of Flowcrete India products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Flowcrete India's products for the Buyer's intended purposes.