

## Flowchem VE SL (3 mm)



### Description

Flowchem VE SL is a horizontal self-smoothing low shrink vinyl ester resin based floor screed system with excellent chemical and mechanical resistance. Applied approx. 3mm thick.

### Uses

For protection of concrete floors and bunds against aggressive chemicals, solvents and thermal attack in medium to heavy duty areas.

### Benefits

- Excellent thermal resistance, up to 145 °C.
- Fast curing – walk on within 12 hours.
- Excellent chemical resistance.
- Excellent abrasion and good impact resistance.
- Hygienic, - smooth and easy to clean.
- Low shrink.

### Project References


Galvanising Plant Floor.

### Colours

Mid Grey, Red and Green.



### System Design



## Model Specification

Product: Flowchem VE SL  
Finish: Satin  
Thickness: 3 mm  
Colour: \_\_\_\_\_  
Manufacturer: Flowcrete India Pvt Ltd  
Telephone: Customer Service - +91 44420 29831  
Preparatory work and application in accordance with manufacturer's instructions.

## Substrate Requirements

Reinforced concrete substrates should be capable of producing 1.5 N/mm<sup>2</sup> "pull-off" values and, following preparation, be free from laitance, dust and other contamination. The substrate should be visibly dry with a moisture content not exceeding 5% by weight, or 75% RH as per BS 8204, and free from rising damp and ground water pressure. If no damp proof membrane is present, Hydraseal DPM can be incorporated directly beneath the Flowchem VE system.

## Products Included in this System

Primer: Flowchem VE Primer@ 0.35 kg/m<sup>2</sup>  
Topping: Flowchem VE SL @ 5.4 kg/m<sup>2</sup> for 3mm.

**NB:** Specifications are written for each installation to meet the client's particular requirements.

## Installation Service

The installation should be carried out by a Flowcrete approved applicator with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our web site at [www.flowcrete.in](http://www.flowcrete.in).

## Focus on the Floorzone

Flowcrete India Pvt Ltd is a division of the Flowcrete Group, world leaders in specialist industrial and commercial flooring. Systems available include: underfloor heating systems, floor screeds, surface damp proof membranes, decorative floor finishes, seamless terrazzo, car park deck waterproofing and corrosion protection systems... to name just a few. Our corporate objective is to satisfy your flooring needs.

## Environmental considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning. Environmental and health considerations are controlled during the manufacture and application of the products by Flowcrete staff and fully trained and experienced contractors.

## Technical Information

The figures that follow are typical properties achieved in laboratory tests at 20 °C and at 50% Relative Humidity.

Slip Resistance

**Dry >40 low slip potential (typical values for 4-S rubber slider)**

Method described in BS 7976-2 (in accordance with HSE and UKSRG guidelines)

The slipperiness of flooring materials can change significantly, due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/ or surface contaminants (wet or dry).

Textured systems are recommended to meet slip resistance value requirements for wet conditions and/ or surface contaminants (wet or dry) - please contact our Technical Advisors for further details and specifications.

Temperature Resistance	<b>145 °C max.</b> – ASTM 648.56
Chemical Resistance	See chart <a href="http://www.flowcrete.com">www.flowcrete.com</a>
Barcol hardness	<b>&gt; 40</b> (ASTM D 2583)
E-Modulus	<b>3.1 GPa</b> (ASTM D 695)
Volume Shrinkage	<b>&lt; 0.004 %</b> Rill 4 2.5.3.2.1
Compressive Strength	<b>120 MPa</b> (ASTM D 695)
Flexural Strength	<b>100 MPa</b> (ASTM D 790)
Tensile Strength	<b>50 MPa</b> (ASTM D 638)
Adhesion	<b>&gt; 4 MPa (Note: Substrate failure)</b>
Density	<b>1.85 approx.</b>

## Speed of Cure

	20 °C
Light traffic	12 hours
Full traffic	24 hours
Full chemical cure	72 hours

The speed of cure can be controlled by varying the accelerator dosage level. The above times are based on the standard dosage level.

## Aftercare - Cleaning and Maintenance

Clean floors regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

## Important Note

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request.

## Further Information

To ensure you are specifying a fit for purpose flooring for your project please consult our Technical Advisors on the number below or visit our website to register your interest in specifying one of the most durable floors on the market.